

Product Bulletin

GF 218

GLOSS WHITE BLOCKOUT VINYL

Removable Adhesive

WindowMark Blockout™ 218 is an 8.0 mil Dual-layer blockout vinyl. The Dual-layer engineering allows for 100% opaque applications where total blockout is required. The 90# liner provides excellent dimensional stability for digital printing. WindowMark Blockout™ 218 accepts a variety of Solvent, Eco-Solvent, Latex, UV Curable common to wide format digital printing systems. Also works well with UV offset & Screen inks.

Applications

This product is recommended for Window Graphics and Retail Displays that require total light blockout without grey or black adhesives being visible on the backside when applied to glass. The 8.0 mil construction makes applications easy and quick.

Thickness

Film 8.0 mils.
Adhesive 0.8 to 1.0 mils.
Liner 6.7 mils.
(Thickness variance +/- 10%)

Dimensional Stability Temperature Ranges

Good
Minimum application temperature +40°F.
Service temperature -40 °F to +180°F.

Expected Exterior Life Removability

3 years (Unprinted).
Removable up to 1 year under normal conditions.

Adhesion

To glass 16 to 32 oz. /in.
To standard test panels 16 to 32 oz. /in.
Tested according to PSTC-101 Method A with 24-hour dwell at 70 °F and 50% relative humidity. Typical values. Individual values may vary. Test thoroughly before production.

Water Resistance Humidity Resistance Storage Stability

Good. Test if immersed.
Good.
Good.

Product Code

218-54 / 54" x 100'
218-60 / 60" x 100'

Recommendations

Completely evaporate inkjet solvents before application. Failure to do so may facilitate solvent penetration resulting in vinyl degradation.



*Manufacturers of
Pressure Sensitive Films*

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537
Web Site: www.generalformulations.com • e-mail: info@generalformulations.com

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions of Sale, Including Disclaimer of Warranties and Limitation of Liability.